

**WHITE CANPRIME
SERIES 3491-100
WHITE****DESCRIPTION:**

WHITE CANPRIME, recognized as our best primer is an acid cured, post catalyzed, white primer ideal for interior use on MDF and solid woodwork. This product is high in solids and has excellent filling, hiding and sanding properties. It demonstrates excellent flexibility and great versatility when tinted. WHITE CANPRIME will provide the end user with a superior finish. This product is low in V.O.C. & H.A.P.S. and meets all KCMA standards.

PRODUCT DATA:

PRODUCT CODE: 3491-100
VISCOSITY (25°C): 80 ± 3 KU
SOLID % by Vol: 39.5 ± 1%
SOLID % by WT: 58.7 ± 1%
VOC: 485 g/L
DENSITY: 1.2336
SHELF LIFE: 12 months

MIXING RATIO:

CATALYST: 448-024 (5% V/V)
REDUCER: 448-890 (10% V/V)
448-880 (15% V/V)
THINNER: 400-017 (20-35%)
2400-017 (20-35%)
RETARDER: 400-068 (1-5%)
400-025 (1-3%)
POT LIFE: 12 Hours

DRYING TIMES:

THICKNESS APPLIED: 5-6 wet mils
DUST FREE: 5-10 minutes
READY TO HANDLE: 20-30 minutes
READY TO SAND: 1 hour minimum

Note: Drying times may vary depending on thickness applied, temperature and/or humidity.

Warning: It is not recommended to use a product whose pot life has expired. A product catalyzed in a metal container can cause discoloration. Total film thickness of the finish should not exceed 5 mils dry film.

APPLICATION:

Surfaces should be clean, oil free and well sanded. Ensure product is stirred thoroughly and mixed according to specifications before applying. Avoid thick coats.

CONVENTIONAL EQUIPMENT:

VISCOSITY: 18-22 sec (FC#4)
TANK PRESSURE: 15-18 PSI
GUN PRESSURE: 45 PSI

AIR ASSIST EQUIPMENT:

VISCOSITY: 18-22 sec (FC#4)
POMP PRESSURE: 50 PSI (20:1 ratio)
AIR PRESSURE: 20 PSI
TIP: 09

AIRLESS EQUIPMENT:

VISCOSITY: 18-22 sec (FC#4)
GUN PRESSURE: 1000-1200 PSI
FINISH THICKNESS: 5-6 mils
NUMBER OF COATS: 1-2

STORAGE:

Store in a dry and cool area. Close the container properly after use.

The customer is responsible for following the recommended application procedures. Failure to adhere to these specifications may result in poor appearance or failure of film. This product is for professional use only. Consult your local representative before applying with other manufacturer products. The customer should test the complete system for adhesion, compatibility and performance prior to full scale application. Please refer to the Safety Data Sheet (SDS) for safety information and precautions prior to using this product. We ONLY guarantee our product to conform to our quality. Our responsibility as manufacturer is limited to the cost of the product. Please feel free to contact us at (819) 367-2201 for any further inquiries regarding this product. All information on this product data sheet is subject to change without notice.